

Personal Protection Fire Blanket Product Data Sheet

Colan's Frontline Personal fire blankets are non woven and made from our PCA fibre, which is inherently fire resistant, will not carry flame and does not melt or drip, is acid & alkaline resistant, UV and solvent resistant.. The blanket is lightweight and suitable to be kept in a car, truck, home or caravan. The Colan PCA blanket has been tested to the AFAC Personal Protective Blanket Specification Version 1.0, 2013.

<u>Test Method</u>	<u>Requirement</u>	<u>Result</u>
Flame Spread ISO 15025-2000		
-Face Ignition	No Holes	Complies
	No molten or flaming debris.	Complies
	Afterflame $\leq 2s$.	Complies
	Afterglow $\leq 2s$	Complies
- Edge Ignition	Char length < 100mm	Complies
	No molten or flaming debris	Complies
	Afterflame $\leq 2s$	Complies
Heat Transfer – Flame Exposure ISO 9151		
- HTI ₂₄	≥ 17 seconds	Av. 28 seconds
- HTI ₂₄ -HTI ₁₂	≥ 4 seconds	Av. 13 seconds
Heat Transfer – Radiant Heat ISO 6942		
- t ₂	≥ 22 seconds	Av. 48 seconds
- t ₂ – t ₁	≥ 4 seconds	Av. 19 seconds
Residual Strength after exposure to radiant heat ISO 13934-1		
Heat Flux Density of 10 kW/m ²	≥ 100 N Warp & Weft	Warp 380 N Weft 500 N
Heat Resistance ISO 17493	No melt, drip, ignition, separation.	Complies
(** Tested at 260 deg C.)	Shrinkage of no more than 5%.	- 6.9%

WEIGHT	506 g/m ² (nominal)	THICKNESS	2.5 mm (nominal)
WIDTH	2.0 mtr (nominal)	LENGTH	1.8 mtr (nominal)
PACKAGING	2 kgs – 45 x 35 x 10 cm	FINISH	Natural
COLOUR	Grey or Red	OKEO-TEX	Class 2 – Next to skin.

• THE FABRIC OF AUSTRALIA •

6 Woods Close Huntingwood NSW 2148 Australia T: +61 2 9672 7888 F: +61 2 9672 7666 W: www.colan.com.au

All information contained in this publication is based upon tests carried out by Colan Products, independent testing authorities or other suppliers. This information is believed to be correct and reliable at time of printing. Colan requires that users establish the suitability of all products for their applications and assume all risks